



### DESCRIPTION:

- 100% acrylic-based non-textured coating.
- Dirt Pick-up Resistance (DPR): The surface of the coating hardens and does not soften again under heat. The non-tacky surface provides high resistance to dirt, mold, and pollutant accumulation.
- Excellent hiding power as well as flexibility and drying characteristics.
- Integrally colored with high-quality pigments.

### USES:

- A protective and decorative exterior or interior coating over concrete, masonry, stucco, or acrylic-based textured finishes. Compatible with Surewall finishes; may be applied over them.
- To promote color uniformity of repaired and modified surfaces.
- To color architectural details and graphics on any of the Surewall finish coatings.
- To recoat existing EIFS.

### COMPOSITION:

- Binder base: 100% acrylic.
- Water-based: VOC-compliant
- Pigment base: Titanium dioxide
- Solids:
  - ◆ By weight: 58%
  - ◆ By volume: 43%
- Color: White or tinted to desired color
- Appearance: Flat, non-gloss, smooth finish

# Elastocoat Smooth Coating

## COVERAGE:

One coat: Approximately 1,000–1,200 ft<sup>2</sup> (106–128m<sup>2</sup>) per pail, depending on the method of application and the surface to which it is applied.

## CONTAINER:

60 lb (27.7 kg) net weight in plastic pails.

- Storage: Protect from sun and freezing at all times.
- Shelf life: One year if protected from sun and freezing.

## DRYING TIME:

Approximately 1–4 hours depending on temperature, humidity, and substrate. Can be recoated after 8 hours. Allow minimum 5 days curing before scrubbing surface.

## CLEANUP:

Water-soluble prior to drying. Clean tools and containers with water prior to drying.

## SURFACE PREPARATION:

- Remove surface contaminants such as dust or dirt without damaging the substrate. For previously painted surfaces, all loose and chalking paint must be removed, and glossy surfaces must be dulled.
- New concrete and masonry must be clean and cured a minimum of 28 days. Check concrete surfaces for alkalinity and treat as needed. Any form-release agents or bond breakers must be removed.
- Uneven concrete or masonry can be leveled with Surewall Prime-A-Flex, Surewall Flex Base Coat, or other suitable, compatible products.
- Drywall: Interior application only. Prepare as for painting.
- For additional options, contact Technical Services.

## MIXING:

- Stir Surewall Elastocoat Smooth to a uniform consistency.
- Avoid creating air bubbles or foam.

## APPLICATION:

- Surewall Elastocoat Smooth exhibits good surface coverage in single applications. However, for most uncoated, unprimed surfaces of concrete, masonry, or drywall, two coats of Surewall Elastocoat Smooth may be required to adequately hide the substrate and obtain optimal performance.
- Surewall Elastocoat Smooth is easily applied with brush, roller, or suitable spray equipment. Apply Surewall Elastocoat Smooth as packaged. If necessary, add a small amount of clean, potable water, maximum 8 oz (1 cup/24L) per pail.

## LIMITATIONS:

- Ambient and surface temperatures must be 40°F (4°C) or higher during application and drying times. Supplemental heat and protection from precipitation must be provided as needed.
- Use only on surfaces that are sound, clean, dry, and free from any residue that might affect the ability of the Elastocoat Smooth to bond to the sur-

Job name \_\_\_\_\_  
\_\_\_\_\_  
\_\_\_\_\_

Contractor \_\_\_\_\_  
\_\_\_\_\_

Date \_\_\_\_\_

**Submittal Approvals:**  
(Stamps or Signatures)

**RES** Architectural Sales, Inc.

143 S. Franklin St., Chagrin Falls, OH 44022 • Phone: Toll Free 888-888-7273 Local 440-247-4070 • Fax 440-247-4069  
Website: [www.resarch.com](http://www.resarch.com) • Email: [sales@resarch.com](mailto:sales@resarch.com)