

SUREWALL®

Elite Finishes

Elite Sand Finish Elite Coarse Sand Elite Rough Trowel Elite Create-a-Finish



DESCRIPTION:

- 100% acrylic-based elastomeric textured finish
- Highly flexible: Can bridge hairline cracks
- Integrally colored with high-quality pigments

USES:

Finishing coat for:

- Surewall FRP
- New or existing stucco and concrete surfaces
- Renovation of old stucco and concrete walls
- Finishing of masonry walls in combination with Flex Base Coat as leveler

COMPOSITION:

- Binder base: 100% acrylic elastomeric polymer with surface-hardening property
- Aggregate: Pure crushed marble, rust-free
- Water-based: VOC-compliant
- Pigment base: Titanium dioxide
- Color: Surewall standard colors or tinted to desired custom color

TESTING:

- Environmental durability: Passes ASTM G 23 resistance to accelerated weathering and ultraviolet test.
- Resistance to wind-driven rain (TT-C-555B): Passes.
- Mildew testing (ASTM D3273): No growth.
- Vapor permeability (ASTM E96): Greater than 10 Perms. Water vapor-permeable; does not create a vapor barrier.

Elite Finishes

Elite Sand Finish Elite Coarse Sand Elite Rough Trowel Elite Create-a-Finish

COVERAGE:

Elite Sand Finish

Aggregate size: 0.75mm
150–165 ft.² (14–15 m²) per pail

Elite Coarse Sand

Aggregate size: 1.5mm
120–135 ft.² (11–12.5 m²) per pail

Elite Rough Trowel

Aggregate size: 1.5mm
120–135 ft.² (11–12.5 m²) per pail

Elite Create-a-Finish

60–150 ft.² (6–14 m²) per pail depending on texture.

Note: Coverage may vary depending on the condition of the substrate, method of application, and finish thickness.

CONTAINER:

65 lb (29.5 kg) net weight in plastic pails.

- Storage: Protect from sun and freezing at all times.
- Shelf life: One year if protected from sun and frost.

DRYING TIME:

48 hours under normal conditions. High humidity and low temperatures extend drying time.

CLEAN-UP:

Water-soluble prior to drying. Clean tools and containers with water prior to drying.

SURFACE PREPARATION

- Over Surewall FRP, portland cement, or plaster: Prime with Pre-Coat Acrylic Primer. Over masonry or concrete: level with Surewall Flex Base Coat or other compatible products and prime with Pre-Coat Acrylic Primer.
- Over painted substrates: Paint must demonstrate adequate adhesion or be removed with methods which result in no more than 10% of the surface having paint remaining. Prime with Pre-Coat Acrylic Primer.
- For application of Pre-Coat Acrylic Primer, refer to the Product Data Sheet.
- For additional options, contact Technical Services.

MIXING:

- Stir to obtain a homogeneous consistency using a heavy-duty 1/2" (13mm) drill with a rust-free paddle at 400–500 r/min. Avoid air entrainment.
- A small amount of clean, potable water may be added to aid workability. Do not exceed 8 oz. (1 cup/.24 L) per full pail of finish. To avoid texture variations, add the same amount of water to each pail of finish.

APPLICATION:

- Always maintain a wet edge and work to corners or joints. For best color consistency, use finish with the same batch number within a wall section. Keep container closed when not in use.
- To apply, use a clean stainless steel trowel and apply a uniform coat the thickness of the largest aggregate size of the finish.
- To texture, use a clean plastic float or stainless steel trowel, wipe frequently, and apply moderate pressure with consistent motion, rolling the large aggregates to obtain the desired texture.

LIMITATIONS:

- Ambient and surface temperature must be 40°F (4°C) or higher during application and drying time. Supplemental heat and protection from precipitation must be provided as needed.
- Use only on surfaces that are sound, clean, dry, unpainted, and free from any residue that may affect the ability of the finish to bond to the surface.
- Avoid application in direct sunlight in hot weather.
- Due to the composition of this product, minor pinholing may be noticeable in the cured finish.

Job name _____

Contractor _____

Date _____

Submittal Approvals:
(Stamps or Signatures)

RES Architectural Sales, Inc.

143 S. Franklin St., Chagrin Falls, OH 44022 • Phone: Toll Free 888-888-7273 Local 440-247-4070 • Fax 440-247-4069
Website: www.resarch.com • Email: sales@resarch.com